

10/526403

DT06 F PCT/PTO 02 MAR 2005

DOCKET NO.: 266456US6PCT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

IN RE APPLICATION OF: Andrew J. WHITEHEAD, et al.

SERIAL NO.: NEW U.S. PCT APPLICATION

FILED: HERewith

INTERNATIONAL APPLICATION NO.: PCT/IB03/03762

INTERNATIONAL FILING DATE: September 4, 2003

FOR: DIAMOND RADIATION DETECTOR

REQUEST FOR PRIORITY UNDER 35 U.S.C. 119
AND THE INTERNATIONAL CONVENTIONCommissioner for Patents
Alexandria, Virginia 22313

Sir:

In the matter of the above-identified application for patent, notice is hereby given that the applicant claims as priority:

COUNTRY
Great Britain**APPLICATION NO**
0220767.8**DAY/MONTH/YEAR**
06 September 2002

Certified copies of the corresponding Convention application(s) were submitted to the International Bureau in PCT Application No. PCT/IB03/03762.

Respectfully submitted,
OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Gregory J. Maier
Attorney of Record
Registration No. 25,599
Surinder Sachar
Registration No. 34,423

Customer Number

22850

(703) 413-3000
Fax No. (703) 413-2220
(OSMMN 08/03)

Best Available Copy



TA 153 1551
Rec'd PCT/PTO

52 MAR 2005

INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

3

1B/03/3762

REC'D 15 OCT 2003

WIPG PGT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.


In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

Signed

Dated 10 September 2003



The
Patent
Office

09SEP02 15:35 / 400019
P01/7700 0220767/8

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

Your reference

PA133734/P (P031711GB)

Patent application number
(The Patent Office will fill in this part)

06 SEP 2002

0220767.8

Full name, address and postcode of the or of
each applicant (underline all surnames)

Diamanx Products Limited
Isle of Man Freeport
Ballasalla
Isle of Man, U.K.
IM99 6AQ

Patents ADP number (if you know it)

07153752002

If the applicant is a corporate body, give the
country/state of its incorporation

Isle of Man, U.K.

Title of the invention

Diamond Radiation Detector

1. Name of your agent (if you have one)

Carpmaels & Ransford

"Address for service" in the United Kingdom
to which all correspondence should be sent
(including the postcode)

43 Bloomsbury Square
London
WC1A 2RA

Patents ADP number (if you know it)

83001

6. If you are declaring priority from one or more
earlier patent applications, give the country
and the date of filing of the or of each of these
earlier applications and (if you know it) the or
each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise
derived from an earlier UK application,
give the number and the filing date of
the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right
to grant of a patent required in support of
this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an
applicant, or
- c) any named applicant is a corporate body

Yes

See note (d))

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form


Description

7

Claim(s)

Abstract

Drawing(s)

2+2 

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

Date


Carpmaels & Ransford

6th September 2002

12. Name and daytime telephone number of person to contact in the United Kingdom

Mr. A.J. Jones

020-7242 8692

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

DIAMOND RADIATION DETECTOR

BACKGROUND OF THE INVENTION

This invention relates to a diamond radiation detector.

Diamond is well known as a potential radiation detector. Its advantages include high radiation hardness, high thermal conductivity, rigidity, and simplicity of the detector design. However, its application has not been as widespread as anticipated, because of a range of practical problems.

Polycrystalline diamond radiation detectors are currently being assessed for a range of applications including particle detectors for the large hadron collider (LHC). In this application, radiation hardness is paramount, but another requirement is good separation of signal from background noise. Based on the particular signal characteristics exhibited by polycrystalline diamond, application of this material requires a charge collection distance (CCD) of at least 250 μm . This value is now just achievable in polycrystalline diamond, but the required grade is substantially more difficult than other polycrystalline grades to manufacture. The 250 μm collection distance is achieved by using very high quality polycrystalline diamond layers about 500 μm thick, and an applied field of 1 V/ μm , equivalent to a voltage of about 500 V. It is found that the CCD in polycrystalline CVD (chemical vapour deposition) diamond rises rapidly with applied field, achieving 90% of saturation at about 0.8 V/ μm and approaching saturation by about 1 V/ μm (i.e. the CCD no longer increases when the field is increased) [see, for example, a) Zhao. S. (1994), PhD Thesis 'Characterization of the Electrical Properties of Polycrystalline Diamond Films', The Ohio State University, b) W Adam et al (The RD42 Collaboration), Nucl. Instr. Methods in Phys. Res. A434 (1999) pp131-145].

Measurements of the CCD of natural single crystal diamond as a function of applied field suggests that it has not saturated even at $2 \text{ V}/\mu\text{m}$ [see, for example, Zhao. S. (1994), PhD Thesis] offering one route to higher CCD values, although exacerbating the problems of using higher voltages. However, the maximum CCD measured with such crystals is reported to be about $40 \mu\text{m}$ at $2 \text{ V}/\mu\text{m}$ applied electric field.

WO 01/96633 discloses a high purity single crystal diamond produced by chemical vapour deposition. The diamond has a high resistivity, a high breakdown voltage in the off state, high electron mobility and hole mobility and a high charge collection distance measured at $1 \text{ V}/\mu\text{m}$. The diamond is described as being useful in electronic applications, particularly as a detector element or switching element.

SUMMARY OF THE INVENTION

It has now been found that the charge collection distance of single crystal CVD diamond, particularly that described in WO 01/96633, rises very rapidly with the applied field, and particularly in samples of the order of $1000 \mu\text{m}$ thick or less, and achieves near saturation (maximum obtainable charge collection distance) at much lower applied fields than $1.0 \text{ V}/\mu\text{m}$. In particular, 90% of the maximum obtainable charge collection distance (i.e. 90% saturation) can be achieved at applied fields as low as $0.25 \text{ V}/\mu\text{m}$.

In use, the benefit is that at $0.25 \text{ V}/\mu\text{m}$ the diamond of the invention can still exhibit CCD values as high as $510 \mu\text{m}$ in samples $550 \mu\text{m}$ thick and operate in a region where the device is not sensitive to small variations in the bias voltage. In contrast, conventional polycrystalline diamond operated at

0.25 V/ μ m would show typically only 70% of the (substantially lower) saturation CCD and be operating in a region where small changes in bias voltage caused large variation in signal, thus degrading device stability and performance.

The invention further provides a detector comprising a single crystal CVD diamond which achieves 90% of saturation with an applied field of less than 0.7 V/ μ m, and preferably less than 0.5 V/ μ m, and more preferably less than 0.3 V/ μ m. The diamond has applied to it a field of less than 0.7 V/ μ m, and preferably less than 0.5 V/ μ m, and more preferably less than 0.3 V/ μ m. With a detector of thickness of 500 μ m, operated at 0.25 V/ μ m, the applied voltage can then be as low as 125 V.

The invention further provides a thin detector element capable of being operated at low bias voltages. In particular, the invention provides a single crystal CVD diamond less than 450 μ m thick, more preferably less than 350 μ m thick and even more preferably less than 250 μ m thick, which achieves 90% of saturation with an applied field of less than 0.7 V/ μ m, and preferably less than 0.5 V/ μ m, and more preferably less than 0.3 V/ μ m. With a detector of thickness of 250 μ m, operated at 0.25 V/ μ m, the applied voltage can then be as low as 63 V whilst still achieving charge collection distances of the order of 250 μ m, as is required for many applications.

Thus the diamond detector of the invention generally exhibits high charge collection efficiency even at these low applied fields, generally achieving values greater than 50%, and typically greater than 75%, and more typically greater than 85%, and even more typically greater than 90%.

The single crystal CVD diamond for use in the invention is preferably high purity single crystal CVD diamond, preferably that described in WO 01/96633, particularly a thin layer of such diamond.

The detector of the invention has particular application in stand-alone, remote or hand-held devices, where provision of high bias voltages may be difficult or costly.

The detector also has particular application where the radiation being detected can be deleteriously scattered, absorbed or otherwise affected by the detector. As the interaction between the radiation and the detector is generally a function of the thickness of the detector element, a thinner detector exhibiting a similar high charge collection distance is beneficial.

DESCRIPTION OF EMBODIMENTS

The invention provides an improved radiation detector that provides useful functionality at lower operating voltages and uses thinner diamond layers compared with existing diamond detectors. The detector can be used for the direct detection of radiation such as beta particles (high energy electrons), alpha particles, protons, other high-energy nuclear particles (pions etc) and high-energy electromagnetic radiation (X-rays, gamma rays etc), and for the indirect detection of neutrons. It is particularly suitable for use in stand-alone hand-held and remote sensor systems.

As mentioned above, the detector of the invention may be used at much lower bias voltages than polycrystalline CVD diamond or natural diamond, for example. The use of lower bias voltages allows the detector to be used in less expensive, simpler systems, and in remote or hand-held devices. For example, a 250 μm thick high purity single crystal CVD diamond detector requires an applied bias of only 63 V to obtain adequate performance. A conventional detector based on a photo-multiplier tube (PMT) would require a supply voltage of, for example, 1 kV to operate. A particular example of remote detection where the reduced voltage would be a considerable benefit is

the 'logging' of wells drilled for oil exploration. Here the detector is in a very hostile environment (both thermally and mechanically) and provision of a high voltage power supply is very difficult. The robust, low voltage, solid-state detector of the invention would be much easier to operate than the conventional high voltage PMT-based detectors.

A further advantage of the detector of the invention is that since the detecting layer is thinner than known polycrystalline diamond and natural diamond detectors, the particles to be detected interact less with, and are thus affected less by, the detector. This is a very important consideration in applications such as high-energy physics (e.g. LHC), where high performance detectors are required, but in addition the radiation being measured may be required to pass through many detector elements essentially unimpeded.

The high purity single crystal CVD diamond layer which is used in the radiation detector of the invention is typically a polished plate between 10 μm and 1000 μm thick, and more typically between 100 μm and 400 μm thick. Ohmic contacts may be formed either on both surfaces, as in a 'sandwich' structure, or on one surface only, as in an interdigitated array. Such ohmic contacts may be formed using methods known in the art.

A dc bias is applied between the two electrodes such that the field is the saturation field of the detector using a high-resistance supply (e.g. Keithley 237 Source-Measure Unit). One electrode is also connected to a charge measuring system, for example a charge sensitive amplifier, so that the signal can be read out.

The detector is placed in a beam of high-energy nuclear particles such as beta particles or pions and the output signal is monitored. When a particle transits the detector, a signal will be detected.

The invention will be illustrated by the following examples.

Example 1

Beta particle or high-energy nuclear particle (e.g. pion) detector.

A conventional diamond particle detector is made from the best available polycrystalline CVD diamond (see for example Adam, W. *et al* (2000), 'Micro-strip sensors based on CVD diamond', Nuclear Instruments and Methods in Physics Research A, 453, 141-148). The detector is 500 μm thick. The detector is irradiated with, for example, beta particles from a strontium-90 source or pions or protons from a particle accelerator beam line. The detector yields, at a saturation bias of 500 V (equivalent to an electric field of 1 V/ μm), about 7000 electrons per particle passing through the detector. This is equivalent to a charge collection efficiency (CCE) of $\sim 39\%$. The charge of 7000 electrons is sufficient for a particle detector to operate with current back-end signal processing electronics.

A layer of high purity single crystal CVD diamond described in WO 01/96633, 500 μm thick, has been found to have a CCE of greater than 95% at 1 V/ μm . Therefore to collect the required 7000 electrons generated by a minimum ionising particle (which generates 36 electron/hole pairs per micron of detector material traversed), the detector only needs to be 210 μm thick. Further, it has been found that such detectors using such a diamond layer of the invention has essentially saturated at a field of 0.3 V/ μm , and achieved 90% saturation at a field of < 0.25 V/ μm . A plot of the saturation curve (measured CCD versus applied voltage) is shown for a 550 μm thick sample in Figure 1. These measurements indicate that it would be possible to reduce the thickness of the detector to 235 μm and the bias voltage to 60 V and still collect 7000 electrons.

Example 2

Alpha particle detector.

A high purity single crystal CVD diamond plate as described in WO 01/96633, about 200 μm thick, was prepared with Ti-Au electrodes on both sides ('sandwich' configuration). It was connected to a 100 V bias and one electrode is connected to a multichannel analyser. The detector was irradiated in vacuum with 5,5 MeV alpha particles from an Americium-241 radioactive source.

The output from the multichannel analyser was a single, narrow peak (full width at half maximum of $\sim 0,18$ MeV) with a signal to noise ratio of approximately 50 (Figure 2). Alpha particle detectors reported made from polycrystalline CVD diamond and reported in the literature (e.g. Foulon, F. *et al* (1998) 'Neutron detectors made from chemically vapour deposited semiconductors', Mat. Res. Soc. Symp. Proc., 487, 591-596) have a broad ill-defined peak that is not useful as a detector. The diamond detector of the invention can thus be used as an alpha particle detector for, for example, well logging.

Example 3

Neutron detector.

A neutron detector is prepared in a similar manner to the alpha detector described in Example 2 except that an additional 'converter layer' of material with a high neutron capture cross section, such as Boron-10, is placed on or adjacent to one electrode. The thickness of the converter layer is typically 0,1 - 10 μm thick. With a boron-10 converter layer, each captured neutron yields an alpha particle. Some of the alpha particles enter the diamond and are detected.

Figure 1





Figure 2



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.